



PRODUCT DECLARATION


SOUND ABSORPTION COEFFICIENT FOR SURFACE

Measured and evaluated according to ISO 354 and ISO 11654

Producer:	Abstracta
Surface:	Air-X (Open)
Total Construction Height:	w = 0

Sound absorption coefficient

f(Hz)	Practical sound absorption coefficient (α_p)
63	0.00
125	0.02
250	0.05
500	0.39
1000	0.73
2000	0.91
4000	0.87



$\alpha_w = 0.35$

ORIGINAL TEST REPORT	DATE OF REPORT
20200904.1	2023-04-23

