PRODUCT DECLARATION


SOUND ABSORPTION COEFFICIENT FOR SURFACE

Measured and evaluated according to ISO 354 and ISO 11654

Producer:	Abstracta
Surface:	Air-X (Closed)
Total Construction Height:	w = 0

Sound absorption coefficient

f(Hz)	Practical sound absorption coefficient (α_p)
63	0.00
125	0.07
250	0.19
500	0.64
1000	0.92
2000	0.94
4000	0.91



α_w = 0.55

ORIGINAL TEST REPORT	DATE OF REPORT
20200904.1	2023-04-23

Acoustic Facts Scandinavia AB
Kinnegatan 23, 531 33 Lidköping