



PRODUCT DECLARATION


SOUND ABSORPTION COEFFICIENT FOR SURFACE

Measured and evaluated according to ISO 354 and ISO 11654

Producer:	Abstracta
Surface:	Aircone
Total Construction Height:	w = 0

Sound absorption coefficient

f(Hz)	Practical sound absorption coefficient (α_p)
63	0.02
125	0.09
250	0.49
500	0.92
1000	1.00
2000	0.95
4000	0.90



$\alpha_w = 0.9$

ORIGINAL TEST REPORT	DATE OF REPORT
13" 137" M7	2013-11-12

