PRODUCT DECLARATION


SOUND ABSORPTION COEFFICIENT FOR SURFACE

Measured and evaluated according to ISO 354 and ISO 11654

Producer:	Abstracta
Surface:	Aircone
Total Construction Height:	w = 0

Sound absorption coefficient

f(Hz)	Practical sound absorption coefficient (α_p)
63	0.02
125	0.09
250	0.49
500	0.92
1000	1.00
2000	0.95
4000	0.90



α_w = 0.9

ORIGINAL TEST REPORT	DATE OF REPORT
13-137-M7	2013-11-12

Acoustic Facts Scandinavia AB
Kinnegatan 23, 531 33 Lidköping