PRODUCT DECLARATION


SOUND ABSORPTION COEFFICIENT FOR SURFACE

Measured and evaluated according to ISO 354 and ISO 11654

Producer:	Abstracta
Surface:	Bits Wall
Total Construction Height:	w = 0

Sound absorption coefficient

f(Hz)	Practical sound absorption coefficient (α_p)
63	0.03
125	0.24
250	0.58
500	0.92
1000	0.97
2000	0.93
4000	0.89



α_w = 0.9

ORIGINAL TEST REPORT	DATE OF REPORT
-	-

Acoustic Facts Scandinavia AB
Kinnegatan 23, 531 33 Lidköping