PRODUCT DECLARATION


SOUND ABSORPTION COEFFICIENT FOR SURFACE

Measured and evaluated according to ISO 354 and ISO 11654

Producer:	Abstracta
Surface:	Soneo Wall
Total Construction Height:	w = 0

Sound absorption coefficient

f(Hz)	Practical sound absorption coefficient (α_p)
63	0.05
125	0.10
250	0.30
500	0.65
1000	0.90
2000	1.00
4000	0.95



α_w = 0.6

ORIGINAL TEST REPORT	DATE OF REPORT
-	-

Acoustic Facts Scandinavia AB
Kinnegatan 23, 531 33 Lidköping