



PRODUCT DECLARATION


SOUND ABSORPTION COEFFICIENT FOR SURFACE

Measured and evaluated according to ISO 354 and ISO 11654

Producer:	Abstracta
Surface:	Airflake Line Closed
Total Construction Height:	w = 100

Sound absorption coefficient

f(Hz)	Practical sound absorption coefficient (α_p)
63	0.00
125	0.00
250	0.00
500	0.10
1000	0.25
2000	0.35
4000	0.45



$\alpha_w = 0.2$

ORIGINAL TEST REPORT	DATE OF REPORT
SP P702033-E	2013-08-12

