PRODUCT DECLARATION


SOUND ABSORPTION COEFFICIENT FOR SURFACE

Measured and evaluated according to ISO 354 and ISO 11654

Producer:	Abstracta
Surface:	Airflake Blade Open
Total Construction Height:	w = 100

Sound absorption coefficient

f(Hz)	Practical sound absorption coefficient (α_p)
63	0.01
125	0.01
250	0.20
500	0.09
1000	0.24
2000	0.33
4000	0.46



α_w = 0.2

ORIGINAL TEST REPORT	DATE OF REPORT
P702033-E	2013-08-19