



## PRODUCT DECLARATION


### SOUND ABSORPTION COEFFICIENT FOR SURFACE

Measured and evaluated according to ISO 354 and ISO 11654

<b>Producer:</b>	Abstracta
<b>Surface:</b>	Airflake Blade Open
<b>Total Construction Height:</b>	w = 100

#### Sound absorption coefficient

f(Hz)	Practical sound absorption coefficient ( $\alpha_p$ )
63	0.01
125	0.01
250	0.20
500	0.09
1000	0.24
2000	0.33
4000	0.46



$\alpha_w = 0.2$

<b>ORIGINAL TEST REPORT</b>	<b>DATE OF REPORT</b>
P702033-E	2013-08-19

